

Structure determination of coinage metal cluster ions by Trapped Ion Electron Diffraction

Detlef Schooß

Institut für Nanotechnologie, Forschungszentrum Karlsruhe, D-76021 Karlsruhe, Germany

The structures of transition metal cluster ions have been studied by the recently developed technique of trapped ion electron diffraction (TIED)¹. In brief, cluster ions are generated by a magnetron sputter source and injected into a cooled (100 K) quadrupole ion trap. After mass selection and thermalization, the trapped ions are irradiated with a 40 keV electron beam. The resulting diffraction pattern is integrated with a CCD detector. The assignment of the structural motif is done via a comparison of the experimental and simulated scattering function, calculated from density functional theory structure calculations.

The structures of mass selected silver cluster cations Ag_{19}^+ , Ag_{38}^+ , Ag_{55}^+ , Ag_{59}^+ , Ag_{75}^+ and Ag_{79}^+ have been investigated². The resulting experimental data are best described by structures based on the icosahedral motif, while closed packed structures could be ruled out. Additionally, we present a comparison of the structures of $\text{Cu}_{20}^{+/-}$, $\text{Ag}_{20}^{+/-}$ and $\text{Au}_{20}^{+/-}$. Our findings show unambiguously that the structure of Au_{20}^- is predominantly given by a tetrahedron in agreement with previous results³. In contrast, structures of Ag_{20}^- and Cu_{20}^- based on the icosahedral motif agree best with the experimental data. The possibilities and limitations of the TIED method are discussed.

- (1) M. Maier-Borst, D. B. Cameron, M. Rokni, and J. H. Parks, Physical Review A **59** (5), R3162 (1999); S. Krückeberg, D. Schooss, M. Maier-Borst, and J. H. Parks, Physical Review Letters **85** (21), 4494 (2000).
- (2) D. Schooss, M.N. Blom, B. v. Issendorff, J. H. Parks, and M.M. Kappes Nano Letters **5** (10), 1972 (2005).
- (3) J. Li, X. Li, H. J. Zhai, and L. S. Wang, Science **299**, 864 (2003).